

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property  
Organization  
International Bureau



(43) International Publication Date  
27 January 2005 (27.01.2005)


PCT

(10) International Publication Number  
**WO 2005/008097 A2**

- (51) International Patent Classification<sup>7</sup>: **F16D 69/02**, C04B 35/83
- (74) Agent: **LAURENCE SHAW & ASSOCIATES LIMITED**; 1 Hagley Road, Edgbaston, Birmingham B16 8TG (GB).
- (21) International Application Number: **PCT/GB2004/002940**
- (81) Designated States (*unless otherwise indicated, for every kind of national protection available*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (22) International Filing Date: **8 July 2004 (08.07.2004)**
- (25) Filing Language: **English**
- (26) Publication Language: **English**
- (30) Priority Data:  
0316530.5 **15 July 2003 (15.07.2003)** **GB**  
10/671,358 **25 September 2003 (25.09.2003)** **US**
- (71) Applicant (*for all designated States except US*): **DUNLOP AEROSPACE LIMITED [GB/GB]**; Holbrook Lane, Coventry CV6 4AA (GB).
- (84) Designated States (*unless otherwise indicated, for every kind of regional protection available*): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).
- (72) Inventor; and
- (75) Inventor/Applicant (*for US only*): **JOHNSON, David, Callum [GB/GB]**; 4 Angless Way, Kenilworth, Warwickshire CV8 1EJ (GB).

[Continued on next page]

(54) Title: **COMPOSITE ARTICLE**



(57) Abstract: A composite article (21) for use in an aircraft brake heat pack, the article comprises a core layer (22) having a face portion and a wear layer (23) attached to the face portion, wherein the wear layer (23) has a density lower than the core layer (22). The core layer (22) may be fabricated from compressed C-C or from C-C impregnated with boron and/or silicon. The wear layer (23) may be fabricated from C-C.

WO 2005/008097 A2



**Published:**

— without international search report and to be republished upon receipt of that report

*For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*

## Composite Article

5           This invention relates to a composite article which exhibits low wear and which has a high heat capacity. Particularly, but not exclusively, the invention relates to a carbon friction disc for use in, say, an aircraft brake.

          For reasons of economic expediency, today's aircraft programmes are  
10   increasingly driven by the need to reduce weight. Such weight reductions allow for an increase in the payload to be carried and/or a reduction in the fuel required to fly the aircraft, both important considerations in times of decreasing or squeezed profit margins and greater environmental awareness.

15           Carbon-carbon composite (C-C) brake discs have become established as the material of choice for aircraft multi-disc brake systems where their relatively high cost is justified by their relatively lower weight compared with the metallic alternative. The high specific heat of carbon allows large quantities of energy to be absorbed by a low brake heat-pack mass during braking.

20

          Early developments in C-C brake discs found that some materials with low wear properties lacked the structural strength needed for the transfer of torque in the brake. A solution to this problem is proposed in US 3,712,427 and US 3,956,548 where low-wear carbon-based wear faces were attached by mechanical means or bonding to a  
25   carbon-based core material.

The high cost of C-C following its introduction as an aircraft brake friction material produced a desire for discs to be suitable for refurbishment and reuse without the need for complete replacement. US 3,800,392 and US 5,558,186 propose systems where wear faces could be removed from a carrier disc at the end of their service life and replaced with virgin material. US 4,982,818 discloses a system wherein the core of a worn disc is split into two and each half is adhered to a virgin core to provide a new friction disc.

The minimum brake heat-pack mass, that is the reject mass at which the brake heat-pack must be removed (brake reject mass) is frequently determined by the energy to be absorbed during the most demanding braking event, the Reject-Take-Off (RTO). The required mass of a new heat-pack is determined by calculating the required reject mass plus an allowance for wearable material that is a function of wear rate per stop and number of stops the brake is required to perform during its service life.

Although a C-C brake heat-pack offers significant weight reduction compared with the metallic alternative, the relatively low density of C-C (typically in the region of  $1.6 - 1.85 \text{ gcm}^{-3}$ ) means the C-C brake heat-pack occupies a large volume that must be supported and accommodated in the surrounding brake chassis and wheel structures.

In the past, C-C brake discs have been infiltrated with molten silicon and heat treated to react at least some of the silicon with the carbon of the matrix to form silicon carbide which improves the friction properties of the so-formed disc. Such materials are known to have a higher density than the C-C of the 'base' disc, the density of the siliconised material being typically in the range  $1.9 - 2.2 \text{ gcm}^{-3}$ . However, the wear rate of such siliconised brake discs is typically significantly higher than that of a

corresponding C-C disc, thus requiring a longer heat-pack of higher density and thereby increasing overall weight of the wheel and brake.

US 6042935 discloses a friction element formed from a core body and a friction  
5 body (wear face) bonded thereto. The friction body is formed of carbon fibre-reinforced porous carbon, the pores of which at least partially being filled with silicon carbide or silicon. The core body may be similarly impregnated with silicon, the friction body thereby having a density which is higher or equal to that of the core body. A joining layer containing silicon carbide may be used to bond the two together.

10

US 2003/0057040 A1 similarly discloses an element in which a friction layer is bonded to a support, the so-formed blank being carbonized and pyrolysed and then infiltrated with silicon to provide a friction layer with in excess of 65% silicon carbide, the friction layer thereby having a higher density than the core layer or support.

15

US 6221475 discloses a friction element having a friction face. The element has, at least in the region of the friction face, a first phase comprising pyrolytic carbon, a second refractory phase and a phase of silicon carbide, to provide a friction face having a density higher than the core.

20

It is an object of this invention to provide a composite article which exhibits an improved capacity for energy absorption and/or a low wear rate in use when in frictional engagement with another composite article of the invention or other article.

25

It is a particular but not exclusive objective of the invention to provide a composite article which is suitable for use as a friction disc in an aircraft brake, the disc having one or both of an improved capacity for energy absorption and a low wear rate

to minimise the weight of a heat-pack and/or to reduce the length of a so-formed heat-pack. It is postulated that by reducing the length of the heat-pack the length of a surrounding brake chassis and other wheel components will be reduced, concomitantly reducing the weight of the aircraft.

5

In a first aspect the invention provides a composite article, for example a brake disc for an aircraft brake heat pack, the, say, disc comprising a core layer having a face portion and a wear layer attached to the face portion, wherein the wear layer has a density lower than the core layer.

10

A second aspect of the invention provides a composite article, for example a brake disc for an aircraft brake heat pack, the composite article comprising a core layer formed from C-C composite impregnated with a refractory carbide, the core layer having a face portion to which is attached a C-C wear layer.

15

There is further provided a method of forming a composite article, for example a brake disc for an aircraft brake heat pack, the method comprising forming a core layer from a relatively higher-density material, the core layer having a face portion, and forming a wear layer from a relatively lower-density material and attaching the wear layer to the face portion of the core layer.

20

A fourth aspect of the invention provides a method of forming a composite article, for example a brake disc for an aircraft brake heat pack, the method comprising forming a C-C core layer with a face portion, densifying the core layer by liquid impregnation; forming a C-C wear layer and attaching the wear layer to the face portion of the core layer.

25

Preferably, the wear layer has a density of from 1.55 to 1.85 gcm<sup>-3</sup>. Preferably the core layer has a density in the range 1.85 – 2.95 gcm<sup>-3</sup>, most preferably in the range of from 2.0 to 2.3 gcm<sup>-3</sup>.

5       The core layer can be densified by impregnation with silicon and/or boron, preferably liquid silicon and/or boron which, in a most preferred embodiment, forms refractory silicon and/or boron carbide through reaction with a carbon matrix comprising at least part of the core layer.

10       The wear layer may be formed from low wearing C-C such as that disclosed in British Patent GB 2,356,642B (held in the name of the current applicant) in which the wear layer is formed from carbon fibres which extend radially from the inner periphery of the wear layer toward or to its outer periphery.

15       A further aspect of the invention provides an aircraft wheel and brake assembly comprising brake discs, one or more of the brake discs having a core layer of density greater than 1.85 gcm<sup>-3</sup> and at least one wear layer attached to the core of density 1.85 gcm<sup>-3</sup> or lower.

20       Preferably, the wear layer is formed of low wearing C-C.

In order that the invention may be more fully understood, it will now be described by way of example only and with reference to the accompanying drawings, in which:

25

Figure 1 is an illustration of a cross section through a prior art C-C brake disc showing regions of wearable carbon;

Figure 2 is an illustration of a cross section through a disc of the invention showing the C-C wear faces bonded to a core;

Figure 3 is an illustration of a cross section through a disc of the invention showing the C-C wear faces worn to reject thickness;

5

Referring to Figure 1, a sectional view of a prior art brake disc for an aircraft multi-disc brake is shown. Here, a C-C rotor brake disc 11 is shown with drive keys (not shown) on the outer periphery thereof for engagement into an aircraft wheel (not shown). The brake disc 11 has two wear surfaces 12, one on each major face of the disc 11 for frictional engagement with discs located either side thereof when installed in a brake assembly. As the disc 11 wears during use, the wear surfaces 12 will progress through the thickness of the underlying material 13 until position 14 is reached, at which point the disc 11 is fully worn and will be replaced.

15 A brake assembly known in the art typically has C-C rotor discs keyed to and rotating with the wheel and interleaved between C-C stator discs keyed to a torque tube which is mounted to the landing gear leg axially around the axle. The assembly of stator and rotor discs is known as a "heat pack". The friction faces of the discs become frictionally engaged when the brake pressure load is applied by the actuator pistons in the brake piston housing. The actuator pistons can be actuated hydraulically or electrically by brake control systems. As the brake friction discs wear at the frictionally engaging surfaces, the thickness of the heat pack is reduced, the reduction in thickness normally being shown by a wear indicator mechanism. When the heat pack reaches its fully worn thickness the heat pack is removed and replaced with new discs.

25 The length of the heat pack at this fully worn condition is known as the reject heat pack length.



Figure 2 is a sectional view through a brake disc 21 of the invention. The density of the core material 22 is higher than  $1.85 \text{ gcm}^{-3}$  (i.e. the density normally known in the art for C-C aircraft brake discs). This is achieved by forming a compressed core of C-C or by forming a usual C-C core and impregnating the same with molten silicon and/or boron. Subsequent to or during impregnation, the elemental silicon and/or boron reacts with the carbon matrix material to form silicon and/or boron carbide. Molten silicon is infiltrated into the C-C core at a temperature of about  $1420^{\circ}\text{C}$  in an inert atmosphere after degassing of the C-C core under a vacuum of  $10^{-1}$  mbar. The Si that is impregnated into the C-C can then be transformed, in whole or in part, to Silicon Carbide (SiC) by reaction with the carbon matrix material in the C-C by heating to temperatures of about  $1800^{\circ}\text{C}$ . Such a core material will typically have a density in the range of  $2.0 - 2.3 \text{ gcm}^{-3}$  depending on the properties of the initial C-C. If the start C-C has a density of  $1.65 \text{ gcm}^{-3}$  and an open porosity of 20% the density after siliconising will typically be a minimum of  $2.1 \text{ gcm}^{-3}$  with 95% conversion of Si to SiC.

15

The wear faces 23, which have a wear surface 24 for frictional engagement, are attached to the core 22 by bonding means at an interface 25 therebetween. The wear faces 23 may be bonded to the core 22 by mechanical means, such as rivets and the like, by chemical bonding agents such as a high temperature brazing alloy, for example Nicrobraz 30 supplied by Wall Colmonoy, by diffusion bonding involving bringing the C-C wear face into intimate contact with the high density C-C core or Si and/or Boron rich core, preferably with pressure applied to maintain the intimate contact, and heating to elevated temperatures in excess of  $1300^{\circ}\text{C}$  to cause bonding between the C-C wear face and core without contaminating the wear face with silicon and/or boron. Bonding can be brought about by the application of a layer of a carbide forming element such as Si or boron at the interface of the core and wear face, the core and wear face then being held in intimate contact during heating in a controlled atmosphere and/or vacuum

25

to a temperature sufficient for the carbide forming element to melt and react with the surface of the wear face and core to form a carbide layer. The temperature for this process is in excess of 1400°C where silicon is used and in excess of 2200°C where boron is used. Alternatively, the wear faces 23 and core 22 may be brought into intimate contact and bonded together by infiltrating with a decomposable carbon-  
5 containing gas and subsequent carbonisation thereof. The decomposable carbon-containing gas could be a hydrocarbon gas such as methane, propane, butane or the like and could be infiltrated into the interface between the core and wear face under vacuum and/or inert atmosphere conditions, the hydrocarbon gas being cracked to  
10 deposit carbon at the interface under temperature and atmosphere conditions known in the art, typically being in the order of 1 mbar vacuum at 1000°C. Such a bonding process has been found to be more effective where a layer of carbon felt is inserted at the interface between the wear face and core.

15 The wear faces 23 have a thickness of wearable material available, the limit of which is shown at position 26. Brake discs 21 are shown with two wear faces 23, however, it will be appreciated that some brake discs might only have one wear face, in particular those stators at the ends of the heat pack. Wear faces 23 could be of C-C material (of, say, density of 1.6 to 1.85 gcm<sup>-3</sup>) or other material having suitable wear  
20 rate and friction properties for application as an aircraft brake disc.

Figure 3 is a sectional view through a brake disc 21 of the invention as shown in Figure 2 with the wear surfaces 24 worn to the wear limit at position 26.

25 To show the benefit derived from the brake discs of the invention, reference is made to the following Examples. In each case, the data refer to an aircraft brake with a brake heat pack comprising 9 discs (4 rotors and 5 stators) designed to fit in a 19"

(482.6 mm) wheel, required to absorb an energy of 63284.520 kJ ( $46.67 \times 10^6$  ft.lbs) during rejected take off (RTO).

5      **Example 1 Brake in C-C (Prior Art)**

	Wear rate of C-C wear faces per landing	2 $\mu$ m (0.00008")
	Number of landings required during service life	1500
	Density of C-C	1.85 gcm <sup>-3</sup>
10	New heat pack length	287.376 mm (11.314")
	Reject heat pack length	238.608 mm (9.394")
	Heat pack weight	47.99 kg (105.8 lb)

15

**Example 2 Brake of the invention**

	Wear rate of C-C wear faces	(2 $\mu$ m) 0.00008"
	Number of landings required during service life	1500
20	Core material density	2.10 gcm <sup>-3</sup>
	Wear face density	1.85 gcm <sup>-3</sup>
	New heat pack length	275.641 mm (10.852")
	Reject heat pack length	227.889 mm (8.972")
	Heat pack weight	47.99 kg (105.8 lbs)

25

Reduction in heat pack length of 0.422" (10.719 mm) is achieved compared with the prior art brake in C-C material to meet the same brake performance specification. This 0.422" (10.719 mm) reduction in heat pack length will allow weight savings in the wheel and brake assembly through a shorter brake torque tube and changes to the wheel design that can be facilitated by the shorter brake length.

The benefits can be improved further using lower wearing wear faces that may not be suitable as brake disc material because they might not meet strength requirements for transfer of torque during braking

10

### Example 3 Brake of the invention

	Wear rate of C-C (low wear rate) per landing	1 $\mu$ m (0.00004")
15	Number of landings required during service life	1500
	Core material density	2.10 gcm <sup>-3</sup>
	Wear face density	1.85 gcm <sup>-3</sup>
	New heat pack length	243.967 mm (9.605")
	Reject heat pack length	227.889 mm (8.972")
20	New Heat pack weight	44.21 kg (97.46 lbs)

Reduction in heat pack length of 43.409 mm (1.709") is provided compared with the (Example 1) prior art brake in C-C material to meet the same brake performance specification. Reduction in heat pack length is more than that provided by Example 2, resulting in further weight savings in the wheel and brake assemblies.

25

The discs of the brake heat pack in Example 1 were manufactured using non-woven reinforcement of the type described in GB 2,012,671 comprising continuous fibres and a layer of staple fibres needled to the continuous fibres. Segments with continuous fibres in the radial and tangential directions were cut from the fabric and laid up in a spiral fashion around a central bung. A segment angle of 48° was used to avoid alignment of segment joints across adjacent layers and segments were alternated between radial fibre direction and tangential fibre direction. The lay-up was continued until sufficient segments had been added to achieve a 20% fibre volume when the central bung was removed and the assembly of segments was compressed to a predetermined volume in a suitable fixture. The assembly was then infiltrated with carbon, by CVI under conditions known in the art, to a density of approximately 1.3 gcm<sup>-3</sup>, taken from the compression fixture and further infiltrated to the density required for a disc density of 1.85 gcm<sup>-3</sup> after heat treatment and machining. The infiltrated discs were then graphitised by heat treating to 2400°C in an inert atmosphere and then machined to final dimensions.

The manufacturing method described above for the C-C brake discs of Example 1 was also used for the C-C wear faces of Example 2. The C-C wear faces of Example 3 differed in that only segments of the radial fibre direction were used in accordance with the brake discs of the invention in GB 2,356,642B.

The core material in Example 2 and Example 3 was manufactured from C-C having non-woven reinforcement of the type described in GB 2,012,671B comprising continuous fibres and a layer of staple fibres needled to the continuous fibres. The fabric is cut into segments or annuli, laid up to the required thickness and weight and compressed into a jig or needled into a preform to a fibre volume of approximately 20%. The assembly of fibres in the jig or the preform is then infiltrated with carbon in

one or more cycles in a chemical vapour infiltration (CVI) process known in the art until a density of 1.60 - 1.65 gcm<sup>-3</sup> was attained. This carbon was then impregnated with silicon which was converted to SiC by reaction with the carbon matrix under conditions known in the art. The resulting siliconised C-C core had less than 5% unconverted  
5 silicon and a density of 2.10 gcm<sup>-3</sup>.

Wear faces were bonded to the cores in Examples 2 and 3 by the use of the braze filler alloy Nicrobraz 30 and by the use of carbon felt infiltrated by CVI.

10 Wear faces bonded to cores with Nicrobraz 30 braze filler alloy had a layer of braze filler alloy applied between the wear faces and core. The discs were held in intimate contact by the application of a pressure of 10psi during heating under a vacuum of 10<sup>-4</sup>mbar to a temperature of 1180°C.

15 Wear faces bonded to cores with a carbon felt infiltrated by CVI had a layer of carbon felt inserted at each of the wear face to core interfaces. The wear face, felt and core surface were held in intimate contact by clamping discs in a fixture before being processed in a CVI furnace under conditions known in the art for the deposition on carbon from a gas comprised mainly of methane. It can assist bonding by this method  
20 if the carbon felt is impregnated with a carbonisable resin that can be heat treated to leave a carbon deposit.

Wear face thickness in Example 2 is 10mm (0.240") and 5mm (0.120") in Example 3. The wear face thickness allows for the required number of landings at the  
25 known wear rate allowing a factor of 2 for uneven wear.

A measure of the savings involved can be shown as the ratio of length of heat pack to overall heat pack weight, viz;

5           **Table 1. Comparison of discs from the Examples**

	<u>Length (L) / mm</u>	<u>Weight (W) / kg</u>	<u>L/W mmkg<sup>-1</sup></u>
Example 1	287.376	47.99	5.99
Example 2	275.641	47.99	5.74
Example 3	243.967	44.21	5.52

Thus, it can be seen that brake heat packs of the invention (Example 2 and 3) provide a respective 4% and 9% reduction over the brake heat pack of the prior art (*i.e.* the ratios of L/W for the respective heat packs).

It will be thus appreciated by the skilled addressee that by using brake heat packs comprising the brake discs of the invention many advantages can be delivered. For example, the length of the new heat pack can be reduced leading to concomitant reductions in wheel and brake weight. Moreover, the use of a bond layer with low thermal conductivity opens the possibility of operating the wear surfaces at a temperature that reduces wear and/or improves friction performance, particularly during aircraft taxi-out when wear in C-C brake discs has been found to be disproportionately high for the brake energy involved.

20

Wear faces on discs running in frictional engagement during service in a brake heat pack could be manufactured from a common C-C wear face blank, cut down to provide wear faces of the required thickness. This would have benefits during the

operation of the brake as friction faces. Wear surfaces with different densities are found to wear at different relative rates, although the overall wear of the brake heat pack is unaffected. In any wear couple with two C-C surfaces the surface with the higher density is found to wear at a higher rate. Some of the benefits of using a high density core are, therefore, lost as the wear face thickness has to include a factor for uneven wear in the heat pack wear faces during service. Balancing the wear face densities by manufacturing from the same blank those faces that will be in frictional engagement would have the advantage of providing even wear across the heat pack during service and reducing any factors built in to the thickness of wear faces to allow for uneven wear.

In addition it will be appreciated that the use of wear faces allows discs to be readily refurbished by the removal of fully worn wear faces and replacement with new faces bonded to the core. Such a refurbishment capability gives considerable economic benefits in the operation of composite brake discs.

It is envisaged that wear faces can be attached to core discs with a flat surface or the wear faces can be attached into a recessed area in the core.

Whilst the invention has been described in relation to aircraft brake discs, it may also be used in, say, clutch discs and other friction discs and the like, where savings of weight are/or size are desirable. In the above-identified applications the discs are solid with internal porosity, *i.e.* there are no through holes for air flow. In some cases such holes may be present. In which case, where the density of the core material is mentioned, it is the density of the actual core material rather than the bulk density of the entire core volume (*i.e.* including the holes) that is referred to.




## Claims


1. A composite article (21) for use in an aircraft brake heat pack, the article (21) comprising a core layer (22) having a face portion and a wear layer (23) attached  
5 to the face portion, wherein the wear layer (23) has a density lower than the core layer.
2. A composite article (21) as claimed in Claim 1, wherein the wear layer (23) is formed from a C-C composite.
- 10 3. A composite article (21) as claimed in Claim 1 or 2, wherein the core layer (22) is a C-C composite article impregnated with a refractory carbide.
4. A composite article (21) for use in an aircraft brake heat pack, the article (21) comprising a core layer (22) formed from C-C composite impregnated with a  
15 refractory carbide, the core layer (22) having a face portion to which is attached a C-C wear layer (23).
5. A composite article (21) as claimed in Claim 3 or 4, wherein the refractory carbide  
20 is silicon carbide or boron carbide.
6. A composite article (21) as claimed in any preceding Claim, wherein the density of the core layer (22) is in excess of  $1.85 \text{ gcm}^{-3}$ .
- 25 7. A composite article (21) as claimed in Claim 6, wherein the density of the core layer (22) is in the range of greater than  $1.85 \text{ gcm}^{-3}$  to  $2.95 \text{ gcm}^{-3}$ .

8. A method of forming a composite article for use in an aircraft brake heat pack, the method comprising forming a core layer from a relatively higher-density material, the core layer having a face portion, and forming a wear layer from a relatively lower-density material and attaching the wear layer to the face portion of the core layer.
9. A method of forming a composite article for use in an aircraft brake heat pack, the method comprising forming a C-C core layer with a face portion, densifying the core layer by liquid impregnation; forming a C-C wear layer and attaching the wear layer to the face portion of the core layer.
10. A method as claimed in Claim 9, comprising densifying the core layer by impregnation with silicon and/or boron,
11. A method as claimed in Claim 10, further comprising converting the silicon and/or boron to the respective refractory carbide by reaction with the C-C matrix.
12. A method as claimed in any of Claims 8 to 11, further comprising forming the wear layer from carbon fibres which extend radially from an inner periphery of the wear layer toward or to an outer periphery thereof.
13. An aircraft wheel and brake assembly comprising brake discs (21), one or more of the brake discs (21) having a core layer (22) of density greater than  $1.85 \text{ gcm}^{-3}$  and at least one wear layer (23) attached to the core (22) of density  $1.85 \text{ gcm}^{-3}$  or lower.

1/2




**Figure 1**



**Figure 2**

2/2



**Figure 3**

## INTERNATIONAL SEARCH REPORT

International Application No

.../GB2004/002940

A. CLASSIFICATION OF SUBJECT MATTER  
IPC 7 F16D69/02 C04B35/83

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 F16D C04B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the International search (name of data base and, where practical, search terms used)

EPO-Internal

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	US 6 042 935 A (KRENKEL WALTER ET AL) 28 March 2000 (2000-03-28) cited in the application column 2, line 14 - line 35 column 4, line 40 - line 54 column 5, line 1 - line 16 claims 1,2,7,11	1-5,8-11
Y	US 2003/057040 A1 (M.BAUER, U.GRUBER, SGL CARBON AG) 27 March 2003 (2003-03-27) paragraph '0006! paragraph '0011! - paragraph '0016!; examples 1,2 & EP 1 273 818 A (SGL CARBON AG) 8 January 2003 (2003-01-08) ----- -/--	1-5,8-11

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

## \* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

26 October 2004

Date of mailing of the international search report

21/01/2005

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax (+31-70) 340-3016

Authorized officer

Boulon, A

## INTERNATIONAL SEARCH REPORT

International Application No

.../GB2004/002940

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	US 6 221 475 B1 (GEORGES JEAN-MICHEL ET AL) 24 April 2001 (2001-04-24) column 2, line 12 - line 28 column 3, line 30 - column 4, line 19 column 9, line 16 - line 33 -----	1-5,8-11
Y	US 2002/068164 A1 (MARTIN ROLAND) 6 June 2002 (2002-06-06) paragraph '0019! - paragraph '0021! -----	1-5,8-11
A	GB 2 356 642 A (DUNLOP AEROSPACE LTD) 30 May 2001 (2001-05-30) cited in the application page 1, line 2 - line 8 page 5, line 10 - page 6, line 2; figure 1 -----	1,12

## INTERNATIONAL SEARCH REPORT

International Application No

.....'GB2004/002940

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 6042935	A	28-03-2000	DE 4438456 A1 WO 9613471 A1 EP 0797555 A1 JP 3053874 B2 JP 10507733 T	02-05-1996 09-05-1996 01-10-1997 19-06-2000 28-07-1998
US 2003057040	A1	27-03-2003	DE 10131769 A1 EP 1273818 A1	06-03-2003 08-01-2003
EP 1273818	A	08-01-2003	DE 10131769 A1 EP 1273818 A1 US 2003057040 A1	06-03-2003 08-01-2003 27-03-2003
US 6221475	B1	24-04-2001	EP 0835853 A1 AT 255545 T CA 2268516 A1 CN 1237950 A , B DE 69726604 D1 DE 69726604 T2 EP 0956276 A1 WO 9816484 A1 JP 2001505863 T KR 2000049126 A RU 2201542 C2	15-04-1998 15-12-2003 23-04-1998 08-12-1999 15-01-2004 30-09-2004 17-11-1999 23-04-1998 08-05-2001 25-07-2000 27-03-2003
US 2002068164	A1	06-06-2002	DE 10066044 A1 EP 1211231 A1 JP 2002255665 A	20-06-2002 05-06-2002 11-09-2002
GB 2356642	A	30-05-2001	WO 0138256 A1 AT 259763 T AU 1286600 A DE 69914959 D1 EP 1233934 A1 US 2001001189 A1	31-05-2001 15-03-2004 04-06-2001 25-03-2004 28-08-2002 17-05-2001